

CHEMICAL RESISTANCE

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
ORGANO-NITROGENS			
Acetonitrile	A		
Aniline	A	B	
Dimethyl Formamide (DMF)	A		
Diethylamine	A		
Nitrobenzene	A		C
Pyridine	A	A	
PHENOLS			
Phenol (Conc.)	C	C	C
Phenol (Dilute)	A		
SULFUR COMPOUNDS			
Carbon Disulfide	A	A	
Dimethylsulfoxide (DMSO)	B	B	
Diphenylsulfone (DPS)	B	C	C
Ethylene Sulfate	A		

KEY

- A — No attack. Little or no absorption.
- B — Slight attack. Satisfactory use of VICTREX PEEK will depend on the application.
- C — Severe attack. VICTREX PEEK should not be used for any application where these chemicals are present.

Dowtherm is a registered trademark of Dow Chemical
 Skydrol is a registered trademark of Monsanto
 Genklene is a registered trademark of ICI
 Freon is a registered trademark of DuPont
 Vaseline is a registered trademark of Chesebrough-Pond's, Inc.

World Headquarters

Victrex plc
 Hillhouse International
 Thornton Cleveleys
 Lancashire FY5 4QD
 United Kingdom
 Tel: +44 (0) 1253 897700
 Fax: +44 (0) 1253 897701
 Email: victrexplc@victrex.com

Americas

Victrex USA Inc
 3A Caledon Court
 Greenville SC 29615
 USA
 Tel: + (1) 800 VICTREX
 Tel: + (1) 864 672 7335
 Fax: + (1) 864 672 7328
 Email: usasales@victrex.com

Europe

Victrex Europa GmbH
 Hauptstr. 11
 65719 Hofheim/Ts.
 Germany
 Tel: + (49) 6192 964949
 Fax: + (49) 6192 964948
 Email: eurossales@victrex.com

Asia-Pacific

Victrex-MC Inc
 Hanai Building 6F
 1-2-9 Shiba Kouen
 Minato-ku
 Tokyo 105 -0011
 Japan
 Tel: +(81) 35777 8737
 Fax: +(81) 35777 8738
 Email: asiapacificsales@victrex.com

Victrex plc believes that the information contained in this brochure is an accurate description of the typical characteristics and/or uses of the product or products, but it is the customer's responsibility to thoroughly test the product in his specific application to determine its performance, efficacy and safety for each end-use product, device or other application. Suggestions of uses should not be taken as inducements to infringe any particular patent. The information and data contained herein are based on information we believe reliable. Mention of a product in this documentation is not a guarantee of availability. Victrex plc reserves the right to modify products, specifications and/or packaging as part of a continuous program of product development.





HIGH PERFORMANCE PEEK™ POLYMERS

VICTREX® PEEK™ POLYMER

CHEMICAL RESISTANCE

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
ACIDS			
Acetic Acid, 10% Conc.	A	A	
Acetic Acid, Conc.	A	A	A
Acetic Acid, Glacial	A	A	
Acrylic Acid	A	A	
Aqua Regia	C	C	C
Benzene Sulfonic Acid	C		
Benzoic Acid	A	A	
Boric Acid	A	A	
Carbolic Acid	A		
Carbonic Acid	A	A	
Chloroacetic Acid	A	A	
Chlorosulfonic Acid	C	C	C
Chromic Acid, 40% Conc.	A		
Chromic Acid, Conc.	C	C	C
Citric Acid	A	A	
Formic Acid	B	B	
Hydrobromic Acid	C	C	C
Hydrochloric Acid, 10% Conc.	A	A	
Hydrochloric Acid, Conc.	A	B	
Hydrocyanic Acid	A	A	
Hydrofluoric Acid, 40% Conc.	C	C	C
Lactic Acid	A	A	
Maleic Acid	A	A	
Nitric Acid, 10% Conc.	A	A	
Nitric Acid, 30% Conc.	B		
Nitric Acid, 50% Conc.	C	C	C
Nitric Acid, Conc.	C	C	C
Nitrous Acid, 10%	A		
Oleic Acid	A		
Oleum	C	C	C
Oxalic Acid	A	A	
Perchloric Acid	A	A	
Phosphoric Acid, 10% Conc.	A	A	A
Phosphoric Acid, 50% Conc.	A	A	A
Phosphoric Acid, 80% Conc.	A	A	
Phthalic Acid	A	A	
Picric Acid	A	A	
Silicic Acid	A	A	
Sulfuric Acid, <40% Conc.	B	B	B
Sulfuric Acid, >40% Conc.	C	C	C
Sulfurous Acid	A	A	
Tannic Acid, 10% Conc.	A	A	
Tartaric Acid	A	A	
Trifluoromethyl Sulfonic Acid	C	C	C

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
ALCOHOLS			
Benzyl Alcohol	A		
Butanol	A		
Cyclohexanol	A		
Ethanol	A	A	
Ethylene Glycol	A	A	B
Ethylene Glycol, 50% Conc.	A	A	A
Glycerol	A		
Glycols	A	A	
Isopropanol	A		
Methanol	A	A	
Propanol	A		
ALDEHYDES/KETONES			
Acetaldehyde	A	A	
Acetone	A	A	
Benzaldehyde	A		
Cyclohexanone	A		
Formaldehyde	A	A	
Formalin	A		
Ketones	A		
Methylethyl Ketone (MEK)	A	B	C
N-Methyl-2-Pyrrolidone (NMP)	A		
BASES			
Ammonia 880	A		
Ammonia Anhydrous	A	A	A
Ammonia Liquid	A	A	A
Ammonium Hydroxide, 10% Conc.	A		
Ammonium Hydroxide, Conc.	A		
Calcium Hydroxide	A		
Hydrazine	A	A	
Hydroxides	A		
Magnesium Hydroxide	A		
Potassium Hydroxide, 10% Conc.	A		
Potassium Hydroxide, 70% Conc.	A		
Sodium Hydroxide, 10% Conc.	A	A	A
Sodium Hydroxide, 50% Conc.	A	A	A
Sodium Hydroxide, Conc.	A		
ESTERS			
Aliphatic Esters	A	A	
Amyl Acetate	A	A	
Butyl Acetate	A		
Dibutyl Phthalate	A		
Dimethyl Phthalate	A		
Diethyl Phthalate	A		
Ethyl Acetate	A		

See key on back

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
ESTERS (cont.)			
Oils (Di-Ester and Phosphate Ester Based)	A	A	
ETHERS			
Diethylether	A	A	
Dioxane	A		
Ether	A	A	
Ethylene Oxide (EtO)	A		
Tetrahydrofuran (THF)	A		
HALOGENATED ORGANICS			
1,1,1 Trichloroethane (Genklene*)	A		
1,2 Dichloroethane	A		
Carbon Tetrachloride	A	A	
Chorobenzene	A	A	
Chloroform	A	A	
Dibromoethane	A		
Dichlorobenzene	A		
Dichloroethane	A		
Ethylene Dichloride	A		
Freon* 11 Trichlorofluoromethane	A		
Freon 113 Trichlorotrifluoroethane	A		
Freon 114 1,1 Dichloro 1,2,2,2 Tetrafluoroethane	A		
Freon 12 Dichlorodifluoromethane	A		
Freon 22 Chlorodifluoromethane	A	A	
Freon 134a	A		
Freon 502	A	A	
Methylene Chloride	A		
Perchloroethylene	A	A	
Trichloroethylene	A	A	
HYDROCARBONS			
Acetylene	A	A	
Aromatic Solvents	A	A	
Aviation Hydraulic Fluid	A		
Benzene	A	A	
Brake Fluid (Mineral)	A	A	A
Brake Fluid (Polyglycol)	A	A	A
Butane	A		
Crude Oil	A		
Cyclohexane	A	A	
Diesel Oil	A		
Dowtherm* A			C
Dowtherm G			B
Dowtherm HT			B
Dowtherm LF			B
Ethane	A		
Fuel Oil	A		
Gas (Manufactured)	A		
Gas (Natural)	A		
Gasoline	A	A	
Heptane	A		
Hexane	A		
Hydraulic Fluid	A		
Iso-Octane	A		

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
HYDROCARBONS (cont.)			
Kerosene	A		
Lubricating Oil	A		
Methane (Gas)	A	A	A
Motor Oil	A	A	A
Naphtha	A	A	
Naphthalene	A	A	
Oils (Petroleum)	A	A	
Oils (Vegetable)	A	A	
Pentane	A		
Petroleum Ether	A		
Propane	A		
Skydrol* Hydraulic Fluid	A		
Styrene (Liquid)	A		
Toluene	A		
Transformer Oil	A	A	
Vaseline*	A		
Xylene	A		
INORGANICS			
Aluminum Chloride	A	A	
Aluminum Sulfate	A	A	
Alum, Saturated	A	A	
Ammonium Chloride, 10% Conc.	A	A	
Ammonium Nitrate	A	A	
Antimony Trichloride	A	A	
Barium Salts (Chloride, Sulfide)	A		
Bleach	A	A	
Brine	A	A	
Bromine	C	C	C
Bromine (Dry)	C	C	C
Bromine (Wet)	C	C	C
Bromine Water, Saturated	A	A	
Calcium Bisulfide	A	A	
Calcium Carbonate	A		
Calcium Chloride	A	A	
Calcium Hypochlorite	A	A	
Calcium Nitrate	A		
Calcium Sulfate	A	A	
Carbon Dioxide (Dry)	A		
Carbon Monoxide (Gas)	A	A	A
Chlorine	C	C	C
Copper Acetate	A	A	
Copper Carbonate	A	A	
Copper Chloride	A	A	
Copper Cyanide	A	A	
Copper Fluoride	A	A	
Copper Nitrate	A	A	
Copper Sulfate	A	A	
Cupric Fluoride	A	A	
Cupric Sulfate	A	A	
Cuprous Chloride	A	A	
Ethylene Nitrate	A		
Ferric Chloride	B	B	
Ferric Nitrate	A		
Ferric Oxide	A	A	

See key on back

CHEMICAL RESISTANCE

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
INORGANICS (cont.)			
Ferric Sulfate	A		
Ferrous Chloride	A		
Ferrous Nitrate	A		
Ferrous Sulfate	A	A	
Fluorine	C	C	C
Hydrogen Peroxide	A	A	
Hydrogen Sulfide (Gas)	A	A	A
Iodine	B		
Lead Acetate	A	A	
Lime	A	A	
Magnesium Chloride	A	A	
Magnesium Sulfate	A	A	
Mercuric Chloride	A	A	
Mercurous Chloride	A		
Mercury	A	A	
Nickel Acetate	A	A	
Nickel Chloride	A	A	
Nickel Nitrate	A	A	
Nickel Salts	A		
Nickel Sulfate	A	A	
Nitrogen	A		
Nitrous Oxide	A		
Oxygen	A		
Ozone	A	B	
Phosphorous Chlorides	A	A	
Phosphorous Pentoxide	A	A	
Potassium Aluminum Sulfate	A	A	
Potassium Bicarbonate	A		
Potassium Bromide	A	A	
Potassium Carbonate	A		
Potassium Chlorate	A	A	
Potassium Chloride	A	A	
Potassium Dichromate	A		
Potassium Ferricyanide	A		
Potassium Ferrocyanide	A		
Potassium Hydroxide	A	A	
Potassium Nitrate	A	A	
Potassium Permanganate	A		
Potassium Sulfate	A	A	
Potassium Sulfide	A		
Silicone Fluids	A	A	
Silver Nitrate	A	A	
Sodium Acetate	A		
Sodium Bicarbonate	A		
Sodium Carbonate	A	A	
Sodium Chlorate	A	A	
Sodium Chloride	A	A	
Sodium Hypochlorite	A	A	
Sodium Nitrate	A	A	
Sodium Nitrite	A		
Sodium Peroxide	A	A	
Sodium Salts	A		
Sodium Silicate	A	A	
Sodium Sulfate	A	A	
Sodium Sulfide	A	A	

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
INORGANICS (cont.)			
Sodium Sulfite	A	A	
Sodium (Hot)	C	C	C
Stannic Chloride	A	A	
Stannous Chloride	A	A	
Steam	A	A	A
Sulfites	A	A	
Sulfur	A	A	
Sulfur Chloride	A	A	
Sulfur Dichloride	A	A	
Sulfur Dioxide	A	A	A
Sulfur Hexafluoride (Gas)	A		
Sulfur Trioxide	A	A	
Tar	A		
Tetraethyl Lead	A		
Water, Distilled	A	A	
Water	A	A	A
Water, Sea/Salt	A	A	
Zinc Chloride	A	A	
Zinc Sulfate	A	A	
MISCELLANEOUS			
Adhesives (not cyanoacrylates)	A		
Apple Juice	A		
Aviation Spirit	A		
Beer	A	A	
Cooking Oil	A		
Creosote	A		
Detergent Solutions (non-phenolic)	A	A	
Edible Fats & Oils	A		
Fatty Acids	A	A	
Fruit Juice	A	A	
Gelatin	A	A	
Ketchup	A		
Linseed Oil	A		
Milk	A	A	
Mineral Oil	A		
Molasses	A	A	
Olive Oil	A	A	
Peanut Oil	A	A	
Paraffin	A	A	
Sewage	A	A	
Soap Solution	A		
Starch	A	A	
Tallow	A	A	
Turpentine	A		
Urea	A	A	
Varnish	A		
Vinegar	A	A	
Wax	A		
White Spirit	A		
Wines and Spirits	A		
Yeast	A	A	

See key on back